



Accura[®] 45HC plastic

for use with SLA[®] 250 systems

A high speed material, with excellent thermal and moisture resistance for producing functional prototypes in 3D Systems' SLA 250 systems.



APPLICATIONS

- High temperature testing:
 - Automotive "under-the-hood" parts
 - Lighting components and accessories
 - HVAC components
- Thin-wall enclosures that require high stiffness and durability
- Parts involved in water-base or high humidity testing
 - Consumer appliance
 - Fluid flow/visualization
- Form, fit and function testing
- General purpose prototyping
- Investment casting using QuickCast™ build style
- Rigid snap-fit assemblies

BENEFITS

Fast build speed

- Provides build speeds that are significantly faster than other resin - up to two times the speed of SL 5170
- Fast build time results in better utilization of your older SL equipment
- Build larger parts than were previously practical with other materials
- Faster delivery to end customers

High temperature resistance combined with good durability

- Suitable for use at temperatures in excess of 100 °C (212 °F)
- Durable enough for limited snap-fit testing

Nylon 6:6 plastic properties

- Suitable for thin-walled parts that require the stiffness of high performance engineering plastics

Parts retain both accuracy and stiffness even in wet and humid environments

- Longer part life with out significant degradation
- Parts that can be used in wet applications such as consumer appliance design, with out excessive softening (or swelling)

Fully developed and tested build styles

- Maximize reliability with no user R&D

Accura[®] 45HC plastic

For use with select SLA[®] 250 systems

Prototype of an electric toothbrush assembly produced with Accura 45HC plastic material.



TECHNICAL DATA

Liquid Material

MEASUREMENT	CONDITION	VALUE:
Appearance		Clear amber
Liquid Density	@ 25°C (77°F)	1.14 g/cm ³
Solid Density	@ 25°C (77°F)	1.2 g/cm ³
Viscosity	@ 30°C (86°F)	475 cps
Penetration Depth (Dp)		5.1 mils
Critical Exposure (Ec)		7.4 mJ/cm ²
Tested Build Styles		FAST [™] , EXACT [™] and QuickCast [™]

Post-cured Material

MEASUREMENT	CONDITION	VALUE:
Tensile Strength	ASTM D 638	59 - 61 MPa (8,520 - 8,860 PSI)
Tensile Modulus	ASTM D 638	2,760 - 2,960 MPa (400 - 430 KSI)
Elongation at Break (%)	ASTM D 638	4.8 - 5.4%
Flexural Strength	ASTM D 790	94 - 101 MPa (13,700 - 14,000 PSI)
Flexural Modulus	ASTM D 790	2,760 - 2,900 MPa (400 - 420 KSI)
Impact Strength (Notched Izod)	ASTM D 256	11 - 16 J/m (0.2 - 0.3 ft-lbs/in)
Heat Deflection Temperature	ASTM D 648 @ 66 PSI @ 264 PSI @ 66 PSI with 160 °C Thermal Postcure	58 °C (136 °F) 51 °C (124 °F) 103 °C (217 °F)
Hardness, Shore D		87
Co-efficient of Thermal Expansion	ASTM E 831-93 TMA (T<Tg, 0 - 20°C) TMA (T>Tg, 90 - 150°C)	72 x 10 ⁻⁶ m/m °C 160 x 10 ⁻⁶ m/m °C
Glass Transition (Tg)	DMA, E''	66 - 87 °C (151- 189 °F)



SYSTEMS

TRANSFORM YOUR PRODUCTS

3D Systems Corporation
333 Three D Systems Circle
Rock Hill, SC 29730 U.S.A.

Tel: 803.326.4080
Toll-free: 800.889.2964
Fax: 803.324.8810

moreinfo@3dsystems.com
www.3dsystems.com
NASDAQ: TDSC

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2007 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. EXACT, FAST and QuickCast are trademarks, and the 3D logo, Accura and SLA are registered trademarks of 3D Systems, Inc.

PN 70603 Issue Date - 06 Sep 07